

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **59107730 A**

(43) Date of publication of application: **22.06.84**

(51) Int. Cl.

B21D 41/04

(21) Application number: **57217558**

(71) Applicant: **SUMITOMO ELECTRIC IND LTD**

(22) Date of filing: **11.12.82**

(72) Inventor: **ONO HIROYOSHI**

(54) TREATMENT OF TERMINAL FOR STRUCTURAL STEEL PIPE

(57) Abstract:

PURPOSE: To enable thorough removal of treating liquid for rinsing, pickling, etc. by water washing, etc. and to make a plating operation safe by half pressing first both ends of a steel pipe to be used for a structure to have the gap to the extent of permitting flow of the plating liquid and molten zinc and subjecting the pressed ends to galvanizing.

CONSTITUTION: The terminal of a steel pipe 1 to be used for a structure is half pressed so as to leave a gap 7 to the extent of permitting outflow of a plating liquid and molten zinc thereby forming a flattened part 6. A bolt hole 8 for coupling is then punched in the part 6. The pipe is dipped in the molten zinc in a molten zinc tank and is thus galvanized. The flat part 6 is pressed again until the inside surfaces of the steel pipe contact tightly with each other.

COPYRIGHT: (C)1984,JPO&Japio

